



NorthStar Red Batteries



Red Star Technology[®] uses advanced Pure Lead AGM electro-chemistry to deliver long float life even at elevated temperatures.

- 15 year float life at 20°C (68°F)
- 4 year float life at 40°C (104°F)
- EUROBAT design life definition: Long Life (12+ years)
- High energy density
- Operating temperature range: -40°C to +65°C (-40°F to 149°F)
- State-of-the-art automated manufacturing ensures consistency and reliability
- Advanced 3 stage terminal design to ensure leak-free operation - brass terminals provide maximum performance
- 2 year shelf life at 25°C (77°F)
- High modulus Polyphenylene Oxide (PPO) plastic materials designed to withstand extended elevated operating temperatures and maintain high battery compression essential for reliable operation
 - Non-halogenated, thermally sealed plastic casing
 - Flame retardant (UL 94 VO) and LOI of at least 28%
- Integral handles and front access terminals ensure ease of installation and maintenance
- Approved as non-hazardous cargo for ground, sea, and air transport - DOT 49CFR173.159(d), (i) and (ii)

SPECIFICATIONS



NSB 13TT Red NSB 125TT Red NSB 40FT Red NSB 60FT Red NSB 92FT Red NSB 100FT Red

Height	129 mm (5.1 in)	275 mm (10.8 in)	208 mm (8.2 in)	263 mm (10.4 in)	264 mm (10.4 in)	287 mm (11.3 in)
Width	82 mm (3.2 in)	173 mm (6.8 in)	97 mm (3.8 in)	108 mm (4.2 in)	108 mm (4.2 in)	108 mm (4.2 in)
Length	175 mm (6.9 in)	345 mm (13.6 in)	250 mm (9.8 in)	287 mm (11.3 in)	396 mm (15.6 in)	396 mm (15.6 in)
Weight	7 kg (16 lbs)	44 kg (97 lbs)	14 kg (31 lbs)	21 kg (45 lbs)	30 kg (66 lbs)	33 kg (72 lbs)
Terminal Torque	6.0 Nm (53 in-lbs)	8.0 Nm (71 in-lbs)	8.0 Nm (71 in-lbs)	8.0 Nm (71 in-lbs)	8.0 Nm (71 in-lbs)	8.0 Nm (71 in-lbs)
1 hr capacity to 1.70 VPC*	10 / 10 Ah	101 / 106 Ah	29 / 30 Ah	44 / 46 Ah	67 / 70 Ah	77 / 81 Ah
3 hr capacity to 1.75 VPC*	12 / 12 Ah	116 / 119 Ah	34 / 35 Ah	51 / 52 Ah	79 / 82 Ah	89 / 92 Ah
8 hr capacity to 1.75 VPC*	13 / 13 Ah	126 / 129 Ah	39 / 39 Ah	58 / 59 Ah	90 / 91 Ah	98 / 100 Ah
10 hr capacity to 1.80 VPC*	13 / 14 Ah	127 / 129 Ah	40 / 40 Ah	59 / 60 Ah	91 / 92 Ah	99 / 100 Ah
Float voltage*	2.29 / 2.27 VPC	2.29 / 2.27 VPC	2.29 / 2.27 VPC	2.29 / 2.27 VPC	2.29 / 2.27 VPC	2.29 / 2.27 VPC
Impedance (1KHz)	11.5 mΩ	2.7 mΩ	4.1 mΩ	4.8 mΩ	3.7 mΩ	3.9 mΩ
Conductance	326 S	1,952 S	1,042 S	965 S	1,344 S	1,298 S
Short circuit current	650 A	3,600 A	1,500 A	2,100 A	3,200 A	3,500 A
Nominal voltage	12 V	12 V	12 V	12 V	12 V	12 V



NSB 110FT Red NSB 155FT Red NSB 170FT Red NSB 190FT Red NSB 210FT Red

Height	227 mm (8.9 in)	280 mm (11.0 in)	320 mm (12.6 in)	320 mm (12.6 in)	328 mm (12.9 in)
Width	125 mm (4.9 in)	125 mm (4.9 in)	125 mm (4.9 in)	125 mm (4.9 in)	126 mm (4.96 in)
Length	560 mm (22.0 in)	560 mm (22.0 in)	560 mm (22.0 in)	560 mm (22.0 in)	560 mm (22.0 in)
Weight	39 kg (86 lbs)	53 kg (117 lbs)	61 kg (134 lbs)	60 kg (132 lbs)	66 kg (145 lbs)
Terminal Torque	8.0 Nm (71 in-lbs)	8.0 Nm (71 in-lbs)	8.0 Nm (71 in-lbs)	8.0 Nm (71 in-lbs)	8.0 Nm (71 in-lbs)
1 hr capacity to 1.70 VPC*	82 / 85 Ah	114 / 119 Ah	126 / 131 Ah	143 / 150 Ah	164 / 171 Ah
3 hr capacity to 1.75 VPC*	97 / 99 Ah	131 / 135 Ah	156 / 160 Ah	171 / 176 Ah	191 / 196 Ah
8 hr capacity to 1.75 VPC*	107 / 109 Ah	148 / 150 Ah	171 / 174 Ah	188 / 191 Ah	207 / 210 Ah
10 hr capacity to 1.80 VPC*	109 / 110 Ah	151 / 154 Ah	172 / 174 Ah	191 / 193 Ah	209 / 212 Ah
Float voltage*	2.29 / 2.27 VPC	2.29 / 2.27 VPC	2.29 / 2.27 VPC	2.29 / 2.27 VPC	2.29 / 2.27 VPC
Impedance (1KHz)	2.6 mΩ	2.3 mΩ	3.3 mΩ	2.6 mΩ	2.7 mΩ
Conductance	1,841 S	2,240 S	1,554 S	2,041 S	2,038 S
Short circuit current	3,800 A	5,000 A	6,000 A	6,000 A	>6,000 A
Nominal voltage	12 V	12 V	12 V	12 V	12 V

* Capacity and float voltages given at 20°C (68°F) and 25°C (77°F)

Delivering reliable and sustainable power to the world.



ADVANTAGES

Pure Lead Thin Plate AGM Technology

Conventional flooded and AGM lead acid batteries use lead alloys with additives which increase the strength so they can withstand the handling during the battery making process. The downside of using these alloys and additives is that the batteries suffer from faster corrosion and component aging. Conventional batteries must also allow space inside the battery for positive grid growth.

The manufacturing process used by NorthStar eliminates the need for lead alloys, additives and wasted space. The plates are inserted into the battery under high compression, which improves performance characteristics, virtually eliminating life limiting failures in high vibration applications.

Unlike conventional batteries, Pure Lead AGM batteries never experience catastrophic failures.



NorthStar Advanced Manufacturing

NorthStar products are designed to be ultra-high performance and premium quality, with a much longer lifetime than standard products. But to build batteries to such a high standard requires the latest robotic processing and manufacturing technology.

That's why we built the industry's most technologically advanced battery manufacturing facilities in Missouri, USA. All NorthStar Red Batteries are proudly made in the USA.

Our facilities are also built and run to meet the toughest possible environmental requirements, to prevent lead poisoning of the surrounding air, ground and water.

Our mission is to deliver reliable and sustainable power to the world. Don't settle for an inferior product - when you need the best, you need a NorthStar Battery.



CONTACTS



NorthStar in the Americas

NorthStar Battery Company LLC
4000 Continental Way
Springfield, MO, 65803,
United States of America
info@northstarbattery.com
Tel: +1 417 575 8200
Fax: +1 417 575 8250

NorthStar in Europe

SiteTel Sweden AB
Staffans Väg 6-8
Box 7039, SE-192 07 Sollentuna
Stockholm, Sweden
europe@northstarbattery.com
Tel: +46 8 410 102 00
Fax: +46 8 638 06 00

NorthStar in Asia-Pacific

NS Asia Pacific Sdn. Bhd.
B2-3A-13A, Solaris Dutamas
No. 1, Jalan Dutamas 1, 50480
Kuala Lumpur, Malaysia
asia@northstarbattery.com
Tel: +60 3 6419 0711

NorthStar in China

Sitetel Sweden AB Shenzhen
International Chamber of Commerce Tower
Fuhua 3rd Road, Futian District
Shenzhen, 518017, China
china@northstarbattery.com
Tel: +86 755 8830 7005

NorthStar in Middle East, Africa

SiteTel Sweden AB JTL Branch
Office 702, Saba 1 Tower
Jumeirah Lake Towers, Dubai
mea@northstarbattery.com
Tel: +971 4 423 8060
Fax: +971 4 423 8061



All NorthStar batteries are compliant with:
Telcordia SR4228, IEC 60 896; Bellcore GR-
63-Core, Issue 1; British, German, and Russian
telecom standards; UL approved. NorthStar is
registered to ISO 9001 and ISO 14001.

www.northstarbattery.com

